

SOLBIN® C5R

TECHNICAL DATA SHEET

Product description

Solbin C5R is a copolymer of vinyl chloride (VC) and vinyl acetate (VAc).

Product characteristics

- Soluble in ketones, esters and chlorinated hydrocarbons. Use aromatic hydrocarbons as diluent solvents. Insoluble in alcohol, oil and aliphatic hydrocarbons.
- Chemically stable and is unaffected by acids and alkalis at normal temperature.
- It combines high water resistance with low moisture permeability and low water absorption.
- Tough, resilient and non-flammable.
- Solbin C5R is colorless and transparent with a high refraction index, it can be changed into any bright color and produces a highly glossy film.
- It possesses an excellent ability to resist the effects of weather and aging.
- As a thermoplastic, films made with Solbin C5R can be easily heat sealed.

General properties

Attributes	Test Results
Appearance	White powder
Grain Size	Passes wholly through 28 mesh sieve
Bulk Density (g/cc)	~ 0.6
Composition (weight %)	
VC	79.0 ± 4.0
VAc	21.0 ± 4.0
Degree of Polymerization	350 ± 50
Molecular Weight Mn	2.7 × 10 ⁴
Glass Transition Temp. (°C)	68
Solution Viscosity (mPa·s)	60 ± 30
Solution Appearance	Colorless, Transparent

Solubility


Solbin C5R is highly soluble in organic solvents such as ketones, esters and chlorinated hydrocarbons.

Solubility of Solbin C5R solutions with various Solvents.

Solvent	25°C	50°C	Solvent	25°C	50°C
Tetrahydrofuran	S	S	Methanol	I	I
Acetone	S	S	Isopropanol	I	I
MEK	S	S	n-Butanol	I	I
MIBK	S	S	Ethylene glycol	I	I
Cyclohexanone	S	S	Methyl acetate	SC	S
Ethylene dichloride	S	S	Ethyl acetate	S	S
Aromatic hydrocarbon	I	SW	Butyl acetate	S	S
Toluene	SW	SW	DIBK	S	S
Xylene	SW	SW	Dioxane	S	S
Aliphatic hydrocarbon	I	I	Isophorone	S	S

Notes: S... Soluble; SC... Soluble but turns cloudy; SW...Swells; I...Insoluble

Viscosity of Solbin C5R solutions with various solvents (@25°C)



SOLBIN C5R

Compatibility with Modifying resins			SOLBIN C5R/ Other			
			9/1	4/1	1/1	1/4
Alkyd	Beckosol ^{*1}	1307-60-EL	O	O	O	X
		1334-EL	O	O	X	X
		1323-60-EL	O	O	X	X
Styrene -Alkyd	Styresol ^{*1}	4250	Δ	Δ	X	X
		4400	Δ	X	X	X
Melamine	Beckamine ^{*1} Superbeckamine ^{*1}	J-138	X	X	X	X
		TD-126	O	O	Δ	X
		J-820	Δ	Δ	X	X
		G-821	O	O	Δ	X
Epoxy	Epikote ^{*2}	828	O	O	O	O
		1001	O	O	Δ	X
Urethane	Nippolan ^{*3}	2300 series	O	O	O	O
		3000 series	O	O	O	O
	Coronate ^{*3}	L	O	O	O	

Coating/film Notes: O-Transparent ; Δ - Slightly clouded;
X- Whitish or knurled. *1—DIC Crop.; *2—Japan Epoxy
Resins Co. Ltd.; *3 Nippon Polyurethane Industry Co., Ltd.

Applications

- Metal Protective Paints—Excellent non-corrosive properties.
- Metal Container Paints—Its anti-corrosive properties make it an excellent choice for lining food and beverage containers, including applications for medicines and cosmetics. It produces a tough film that makes it ideal for coating steel and galvanized tin plates that will be fabricated later.
- Paper and Textile Coating—Waterproof properties adds gloss for a better decorative effect.
- Ship Paints—Exceptionally high anticorrosive properties make it ideal for topcoat as well as wash primer and second coat applications.
- Cellophane coating—SOLBIN C5R is damp-proof, its film is readily heat sealed, ideal for coating cellophane.
- Concrete and Plaster Paints—Coating the walls of quays.
- Adhesives—Recommended as a PVC adhesive.
- Plastic coatings—Adds gloss to both coating and gravure printing ink on plastic.

How to Use

- To ensure Solbin C5R quickly goes into solution it is recommended to disperse it into a weaker solvent such as toluene and xylene then blend with the stronger solvent.
- Solbin C5R is usually dissolved in a combination of both ketone (e.g. MEK and MIBK) and aromatic hydrocarbon (e.g. toluene and xylene) solvents in equal proportions, to produce a solution of 15% - 20% concentration by weight. For coatings on a porous substance, (paper or

cloth), faster drying solvents such as MEK and acetone are recommended.

- For Spray coating, MIBK is used. For baking on metals, ketone with a high boiling point such as cyclohexanone is used. For roll coatings, cyclohexanone or isophorone are sometimes used. Heating to around 50°C and sufficient agitation are required to speed up dissolving.
- In order to provide proper flexibility, resilience and adhesiveness to film, 5-10 PHR of plasticizer are added. Plasticizers used for blending polyvinyl chloride resins are all applicable.
- Stabilizers against heat and light are used, as with conventional polyvinyl chloride resins. The addition of about 0.2% propylene oxide, in this case, can prevent the corrosion of containers and change in paints in storage.
- Any method of coating, including spraying, roll coating and others, may be used. For roll coating, a solution of 200-400 seconds in Ford Cup No.4 viscosity should be used. For Spray applications a solution of 60-80 seconds Ford Cup No.4 viscosity should be used at an air pressure of 98-100psi and a liquid pressure of 20-30psi.
- Solbin C5R does not usually provide satisfactory adhesion through air drying alone. The following chart provides the degree of adhesion to various surfaces by air drying:

Excellent	Polyvinyl chloride resin, Acryl resin
Good	Concrete, Plaster
Fair	Chlorinated rubber
Inferior	Metal, Wood, Paper, Cloth, Phenol resin, Alkyd resin, Butyral resin, Celluloid, Shellac, Dried waterborne or oil paints

- Short-time baking at 170-190°C will significantly improve adhesion and surface gloss. When primers are used, sufficient adhesion may be obtained without baking.

Please contact: Shin-Etsu MicroSi

1.888.642.7674 www.microsi.com

Nissin Chemical Industry Co., Ltd.

+81.3.3295.3931 www.nissin-chem.co.jp



Caution

- ◆ Follow the precautions in the material safety data sheet and technical references.
- ◆ SOLBIN is for industrial use only.
- ◆ The data in this document does not include all specifications. Purchasers must conduct tests of their own before putting the product to practical use to verify its compliance, with their intentions for its employment.
We give no guarantee that the uses presented in this document do not come in conflict with any patents. For the purpose of enhancement of performance or change of specifications, the contents in this document are subject to revision without notice.
- ◆ Permission is required to reprint our data.